

Technique was achieved by brushing on two (2) layers of base glaze. Then apply two (2) layers of top glaze (SW-185 Rainforest) to the top 1/4 of piece, letting glazes dry between coats.





Vases shown are fired to Cone 6 on White Stoneware body.

Mayco

MaycoColors.com



Technique was achieved by brushing on two (2) layers of base glaze. Then apply two (2) layers of top glaze (SW-185 Rainforest) to the top 1/4 of piece, letting glazes dry between coats.





Vases shown are fired to Cone 10 reduction on White Stoneware body.



MaycoColors.com