

# TAKE YOUR COSMOS TO THE NEXT LEVEL



While these glazes can produce crystalline glaze effects with no special schedules, using a controlled cooling schedule can increase crystal growth and take your glazes to the next level!

Also, the chemistry of these gorgeous glazes makes them prone to pinholing. We have a couple ways to counter this:

1. Use on a narrow neck or closed form and DO NOT glaze the inside. This will allow gasses to escape through the unglazed area.
2. If the inside and outside of the pot is glazed, we recommend this firing schedule (see below):

## COSMOS UP-DOWN FIRING SCHEDULE

RAMP SEGMENT	RATE (FAHRENHEIT)	TEMP (FAHRENHEIT)	HOLD
1	400°	2000°	0:00
2	120°	2225°	0:00
3	9999°	1600°	0:00
4	400°	2000°	0:00
5	120°	2160°	0:05

Vases are CO-14 Solar Rainbow on AMACO A-Mix White Stoneware No.11.



Normal Cone 6, glazed inside and out



1. Normal Cone 6, unglazed inside



2. Up-Down Schedule, glazed inside and out